

INDUSFALT 20/30

Asphaltic bitumen obtained by direct distillation or other refining methods specifically designed to be used as base in industrial products.

SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Softening point (R&B)	°C	EN 1427	55	63
Penetration (25°C)	0,1 mm	EN 1426	20	30
Penetration (25°C)	%	EN 12592	99	--
Loss in mass after heating	%	EN 13303	-	0,5
Flash point	°C	EN ISO 2592	240	--

RECOMMENDED WORKING TEMPERATURES

> Pumping temperature (°C): 120 - 160.